

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>C09J 123/10, 151/06</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 95/24449</b> <b>(43) International Publication Date:</b> 14 September 1995 (14.09.95)
<b>(21) International Application Number:</b> PCT/CA95/00132 <b>(22) International Filing Date:</b> 10 March 1995 (10.03.95)  <b>(30) Priority Data:</b> 9404708.1 11 March 1994 (11.03.94) GB  <b>(71) Applicant (for all designated States except US):</b> DUPONT CANADA INC. [CA/CA]; Box 2200 Streetsville, Mississauga, Ontario L5M 2H3 (CA).  <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> ARTHURS, Trevor, Curtis [CA/CA]; 69 Meadowland Avenue, Truro, Nova Scotia B2N 6J9 (CA). KELLY, Peter, Yates [AU/CA]; Box 866, Kingston, Ontario K7L 4X6 (CA). BRYCE, Wayne, Frederick [CA/CA]; 2 Eren Court, Box 10, Camlachie, Ontario N0N 1E0 (CA). MITCHELL, David, John [CA/CA]; 242 Willindon Avenue, Kingston, Ontario K7L 4J1 (CA).  <b>(74) Agent:</b> GALLOWAY, Warren, J.; Sim & McBurney, Suite 701, 330 University Avenue, Toronto, Ontario M5G 1R7 (CA).		<b>(81) Designated States:</b> AU, CA, JP, MX, US, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> POLYPROPYLENE-BASED HOT-MELT ADHESIVE		
<b>(57) Abstract</b>  An adhesive composition comprising a melt blend of: (a) 50-95 % by weight of polypropylene that has been grafted with 0-5 %, especially at least 0.1 % by weight, of at least one ethylenically-unsaturated carboxylic acid or anhydride, or derivative thereof; and (b) 5-50 % by weight of at least one copolymer of ethylene and at least one comonomer selected from carbon monoxide, vinyl acetate, alkyl acrylates, alkyl methacrylates, in which the alkyl group has 1-4 carbon atoms, acrylic acid and methacrylic acid, and ethylene/propylene/diene copolymers, said copolymer having been grafted with 0-5 % by weight of at least one ethylenically-unsaturated carboxylic acid or anhydride, or derivative thereof. The adhesive composition has a melt viscosity suitable for use as a hot melt adhesive.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgistan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

POLYPROPYLENE-BASED HOT-MELT ADHESIVE

The present invention relates to a polypropylene-based hot-melt adhesive composition which is capable of bonding a polypropylene substrate to another substrate. In particular, the present invention relates to a polypropylene-based hot-melt adhesive composition that is capable of being applied so as to bond two polypropylene-based substrates together and also be capable of being subjected to recycling processes for polypropylene.

Structures may be bonded together using a variety of adhesives. One adhesive that is relatively easy to apply while still providing good bonding properties is an isocyanate-containing polyurethane adhesive, which may be sprayed onto a substrate and then subsequently cured to provide a strong bond strength. In particular, use of water-based polyurethane adhesives is known for the bonding of polypropylene substrates to another substrate e.g. the bonding of mica-filled polypropylene to a woven polyester fabric. However, the use of such polyurethane adhesives in lamination processes represents an occupational health risk and major precautions must be taken during operation of the process in order to protect the personnel involved. It would be desirable to have alternate processes that do not use polyurethane adhesives.

The grafting of ethylenically-unsaturated carboxylic acids or anhydrides onto polyolefins is described in U.S. Patent 4 612 155 of R.A. Zelinka and C.S. Wong, which issued September 16, 1986.

U.S. Patent 5 241 014 of H. Kehr et al. discloses the production of largely amorphous polyalpha-olefins with a narrow molecular weight distribution by subjecting largely amorphous polyalpha-olefins containing 3-75 weight percent of

- 2 -

C<sub>4</sub>-C<sub>10</sub> alpha-olefin, 25-95 weight percent of propylene and 0-20 weight percent ethylene monomer units to a shearing force at a temperature above the softening point of the polymer in the presence of a radical donor. Grafting reactions may be conducted at the same time. The polymers are stated to be useful as hot-melt adhesives.

U.S. Patent 4 719 260 of R.K. Stuart et al. discloses hot-melt adhesive compositions useful for bonding polyethylene, that contain amorphous polypropylene polymers and grafted copolymers of saturated polycyclic hydrocarbon resins and maleic anhydride. U.S. 4 554 304 of D.R. Hansen et al. discloses hot-melt adhesive compositions formed from butene/ethylene copolymers that have been grafted with maleic anhydride and aliphatic non-polar resins.

An adhesive has been found that is capable of bonding one polypropylene substrate to another substrate, especially mica-filled polypropylene, foam polypropylene or a woven polypropylene, and be capable of being recycled with polypropylene.

Accordingly, the present invention provides an adhesive composition comprising a melt blend of:

(a) 50-95% by weight of polypropylene that has been grafted with 0-5% by weight of at least one ethylenically-unsaturated carboxylic acid or anhydride, or derivative thereof; and

(b) 5-50% by weight of at least one copolymer of ethylene and at least one comonomer selected from carbon monoxide, vinyl acetate, alkyl acrylates, alkyl methacrylates, in which the alkyl group has 1-4 carbon atoms, acrylic acid and methacrylic acid, and ethylene/propylene/diene copolymers, said ethylene/propylene/diene copolymer having a Mooney viscosity of less than 20 at 125°C, said copolymer having been grafted with 0-5% by

weight of at least one ethylenically-unsaturated carboxylic acid or anhydride, or derivative thereof.

In a preferred embodiment of the blend of the invention, the blend is in the form of a melt  
5 blend.

In another embodiment, the grafted copolymer of (a) has a melt index in the range of 100-500 dg/min.

In further embodiments, the copolymers of  
10 (a) and/or (b) are grafted copolymers. In particular, grafted copolymer (b) has a melt index of at least 100 dg/min.

In still another embodiment, the copolymer of (b) has been grafted with 0.5-2.0% by weight of  
15 the ethylenically unsaturated carboxylic acid or anhydride, or derivative thereof.

The present invention also provides an adhesive composition comprising a blend of:

(a) 50-95% by weight of polypropylene; and  
20 (b) 5-50% by weight of at least one copolymer of ethylene and at least one comonomer selected from carbon monoxide, vinyl acetate, alkyl acrylates, alkyl methacrylates, in which the alkyl group has 1-4 carbon atoms, acrylic acid and  
25 methacrylic acid, and ethylene/propylene/diene copolymers, said ethylene/propylene/diene copolymer having a Mooney viscosity of less than 20 at 125°C, said blend having been grafted with 0-5% by weight of at least one ethylenically-unsaturated  
30 carboxylic acid or anhydride, or derivative thereof.

In embodiments of the adhesive compositions of the invention, the adhesive composition contains un-grafted ethylene/vinyl acetate copolymer or ethylene/propylene/diene copolymer, especially such  
35 ungrafted copolymer in the presence of grafted copolymer of (b).

- 4 -

In other embodiments, the copolymer of (b) is selected from ethylene/vinyl acetate copolymers, ethylene/(meth) acrylate copolymers, ethylene/(meth) acrylic acid copolymers, and copolymers of ethylene, alkyl acrylate and carbon monoxide.

In addition, the present invention provides a process for the bonding of a first substrate to a second substrate comprising coating the first substrate with a molten composition of a blend of:

(a) 50-95% by weight of polypropylene that has been grafted with 0-5% by weight of at least one ethylenically-unsaturated carboxylic acid or anhydride, or derivative thereof; and

(b) 5-50% by weight of at least one copolymer of ethylene and at least one comonomer selected from carbon monoxide, vinyl acetate, alkyl acrylates, alkyl methacrylates, in which the alkyl group has 1-4 carbon atoms, acrylic acid and methacrylic acid, and ethylene/propylene/diene copolymers, said ethylene/propylene/diene copolymer having a Mooney viscosity of less than 20 at 125°C, said copolymer having been grafted with 0-5% by weight of at least one ethylenically-unsaturated carboxylic acid or anhydride, or derivative thereof; contacting the second substrate with the molten adhesive and cooling the resultant bonded structure.

Furthermore, the present invention provides a process for the bonding of a first substrate to a second substrate comprising coating the first substrate with a molten composition of a blend of:

(a) 50-95% by weight of polypropylene and  
(b) 5-50% by weight of at least one copolymer of ethylene and at least one comonomer selected from carbon monoxide, vinyl acetate, alkyl acrylates, alkyl methacrylates, in which the alkyl group has 1-4 carbon atoms, acrylic acid and

methacrylic acid, and ethylene/propylene/diene copolymers, said ethylene/propylene/diene copolymer having a Mooney viscosity of less than 20 at 125°C;

5       said blend having been grafted with 0-5%, especially 0.5-2.0%, by weight of at least one ethylenically-unsaturated carboxylic acid or anhydride;

10       contacting the second substrate with the molten adhesive and cooling the resultant bonded structure.

15       In preferred embodiments of the processes of the present invention, at least one and preferably both of the substrates is formed from polypropylene, including mineral-filled, foamed or woven polypropylene.

20       A variety of polyolefins may be used in the adhesive of the present invention, as defined above. Different polyolefins are used for the components described as (a) and (b) above, and those polyolefins in the form used in the adhesive must be compatible in order that the resultant adhesive has acceptable properties.

25       The copolymer of component (a) is polypropylene. As used herein, the expression "polypropylene" refers to homopolymers of propylene, to impact or so-called block copolymers of propylene with ethylene in which the ethylene content is less than about 25% by weight and to random copolymers of propylene with ethylene in which the ethylene content is less than about 8% by weight.

30       The copolymer of component (b) may be a copolymer of ethylene and at least one comonomer selected from carbon monoxide, vinyl acetate, alkyl acrylates, alkyl methacrylates, in which the alkyl group has 1-4 carbon atoms, acrylic acid and methacrylic acid. In embodiments, the copolymer of component (b) is a copolymer of ethylene, alkyl

acrylate and carbon monoxide. In other embodiments, the copolymer is characterized by having a heat of crystallization of less than 70 J/g. Moreover, if the copolymer is an ethylene/vinyl acetate copolymer, then the copolymer has a vinyl acetate content of at least 10% by weight. Examples of the copolymers are ethylene/vinyl acetate copolymers, ethylene/methyl acrylate copolymers, ethylene/ethyl acrylate copolymers, ethylene/butyl acrylate copolymers, ethylene/isobutyl acrylate copolymers, ethylene/vinyl acetate/carbon monoxide copolymers, ethylene/ethyl acrylate/carbon monoxide copolymers, ethylene/butyl acrylate/carbon monoxide copolymers, ethylene/ethyl methacrylate/carbon monoxide copolymers and ethylene/butyl methacrylate/carbon monoxide copolymers. While the copolymer of (b) may be used in an un-grafted state, it is preferred that the copolymer be grafted.

The monomer used in the grafting of the copolymers is at least one monomer selected from ethylenically unsaturated carboxylic acids and ethylenically unsaturated carboxylic acid anhydrides, including, less preferably, derivatives of such acids, and mixtures thereof. Examples of the acids and anhydrides, which may be mono-, di- or polycarboxylic acids, are acrylic acid, methacrylic acid, maleic acid, fumaric acid, itaconic acid, crotonic acid, itaconic anhydride, maleic anhydride, and substituted maleic anhydride, e.g. dimethyl maleic anhydride or citraconic anhydride, nadic anhydride, nadic methyl anhydride, and tetrahydrophthalic anhydride, maleic anhydride being particularly preferred. Examples of the derivatives of the unsaturated acids are salts, amides, imides and esters e.g. mono- and disodium maleate, acrylamide, maleimide, glycidyl methacrylate and dimethyl fumarate. Techniques for the grafting of



such monomers onto the copolymers are known e.g. as described in U.S. Patent 4 612 155 of R.A. Zelonka and C.S. Wong, which issued September 16, 1986, and in published European patent application No.

5 0 369 604 of D.J. Mitchell, published May 23, 1990. The present invention will be particularly described herein with reference to maleic anhydride as the grafting monomer.

10 Alternatively, the copolymer of (b) may be grafted or ungrafted copolymer of ethylene, propylene and a diene i.e. the so-called EPDM copolymers. Such copolymers have a Mooney viscosity of less than 20 at 125°C.

15 The adhesive composition of the present invention has a melt viscosity suitable for use as a hot melt adhesive, especially a melt viscosity of 1000-100 000 cps at 220°C, especially 10 000-75 000 cps at 220°C, and particularly 20 000-50 000 cps at 220°C. Melt viscosity is measured using a Brookfield  
20 viscometer at a shear rate of 0.35 sec<sup>-1</sup>.

The melt index of the grafted copolymer of (a), when prepared separately, is preferably in the range of 100-500 dg/min, and especially 200-400 dg/min; as used herein, melt index is measured by the  
25 procedure of ASTM D-1238 (190/2.16, unless specified to the contrary). The grafted monomer content of the copolymer of (a), when prepared separately, is 0-5% by weight, especially at least 0.1% by weight, and in particular at least 0.5% by weight. In embodiments,  
30 the amount of grafted monomer is 0.5-2.0% by weight.

The melt index of the grafted copolymer or, where applicable, the ungrafted copolymer of (b), when prepared separately, is preferably at least 100 dg/min, and especially at least 250 dg/min. The  
35 grafted monomer content of the copolymer of (b), when prepared separately, is 0-5% by weight and especially

0.1-2% by weight. In embodiments, the amount of grafted monomer is 0.5-2.0% by weight.

It is also known to use blends of grafted and ungrafted polyolefins to order to achieve a desired level of graft in a composition, and such blending in of ungrafted components may be used herein.

The adhesive composition of the present invention may be in the form of a physical admixture of the grafted copolymers of (a) and (b) described above. Such a physical admixture could be fed to a hot melt adhesive applicator. However, it is preferred that the adhesive composition be melt blended prior to being fed to the hot melt adhesive applicator, including for reasons of consistency of the adhesive composition that is actually applied to a substrate. Alternatively, the respective copolymers of the adhesive composition may be blended and then the blend subjected to a grafting process, using the monomers described herein, under melt conditions.

The adhesive is extruded directly onto a substrate i.e. while the adhesive is still in a molten condition. Apparatus suitable for the blending or mixing of the adhesive and for application of a hot melt adhesive to a substrate are known.

The adhesive is applied to a first substrate in a molten condition and then the second substrate is applied over the adhesive while the adhesive is still in a molten condition. Contact of the adhesive while molten with both substrates is important in order to achieve a good bond.

While a variety of substrates may be bonded together using the adhesive composition described herein, in preferred embodiments at least one and especially both substrates are formed from

- 9 -

polypropylene. Examples of particularly preferred substrates are mineral-filled polypropylene e.g. mica-filled polypropylene, foamed polypropylene, and woven polypropylene including fabrics, woven tapes and the like.

The adhesive composition and process of the invention may be used in the bonding of substrates, especially polypropylene. In the latter instance, use of the adhesive composition permits the opportunity of recycling the bonded substrates as the polymeric components are based on or compatible with polypropylene. Such polypropylene would have a melt index (or melt flow index) and other characteristics of polypropylenes used in the forming of articles, which would depend in part on the particular end-use.

The adhesive forms strong bonds with polypropylene, as illustrated below, but may be used with other substrates. The adhesive may be used in a wide variety of industrial applications, including for example in the automotive industry, and in the manufacture of furniture, appliances and small electronic equipment.

The present invention is illustrated by the following examples:

EXAMPLE I

A random copolymer of propylene with 4% of ethylene as comonomer and having a melt flow index (procedure of ASTM D1238 (230/2.16)) of 5 dg/min was grafted with 1.4% by weight of maleic anhydride using a melt grafting process and a free radical initiator. The melt index of the grafted copolymer obtained was 260 dg/min. This grafted copolymer is referred to below as component A.

An ethylene/vinyl acetate copolymer containing 28% by weight of vinyl acetate comonomer and having a melt index of 800 dg/min was grafted with 0.8% by weight of maleic anhydride using a melt

- 10 -

grafting process and a free radical initiator. This grafted copolymer is referred to below as component B, and had a melt index after grafting of 400 dg/min.

Component C was an ethylene (70% by weight)/propylene (23% by weight)/hexadiene (4.4% by weight)/norbornadiene (1% by weight) polymer that had been grafted with maleic anhydride. The grafted polymer had a Mooney viscosity at 125°C of 22.

Component D was an ethylene (70% by weight)/propylene (23% by weight)/hexadiene (4.4% by weight)/norbornadiene (1% by weight) that had been grafted with maleic anhydride. The grafted polymer had a Mooney viscosity at 125°C of 10.

A series of hot-melt adhesives were prepared using component A. The adhesive was prepared using a Brabender mixer to melt blend component A with another polymeric component, were applicable, and cooled. The resultant adhesive was applied, using a hot melt adhesive applicator, to a mica-filled polypropylene sheet, formed from homopolymer polypropylene containing 35% by weight of mica. After application of the hot-melt adhesive to the mica-filled polypropylene sheet, the adhesive while still molten was contacted with either a polyethylene terephthalate (PET) woven fabric or a foamed polypropylene sheet.

The bonded substrates were then subjected to two tests viz. a room temperature 180° peel test and a 95°C creep test. The test procedures were as follows:

The 180° Peel Strength was determined using samples measuring 2.54 cm by 7.6 cm were peeled apart at ambient temperature, by peeling the substrates apart at an angle of 180° at a speed of 200 mm/min. The results are reported in lb/in.

The creep test involved holding one substrate in a horizontal position and attaching a

- 11 -

200 g weight to the other substrate. The weight was permitted to hang freely, forming a 90° angle to the horizontal substrate. The samples were the same size as those for the peel strength test. The samples being tested were placed in an oven at 95°C shortly after preparation. To pass this test, at least 80% of the samples tested must not show signs of creep after a period of seven days.

The results obtained were as follows:

10

TABLE I

Polymeric Component*	Substrate	180° Peel Strength	Failure Type	Creep Test
B	PET fabric	26.8	cohesive	passed
B	PP foam	7.8	substrate	passed
15 C	PET fabric	23.0	cohesive	failed
D	PET fabric	27.6	cohesive	passed
none	PET fabric	23.6	adhesive	-

\* The amount of Component A in all samples was 80% by weight, except the last sample where the amount was 100% by weight i.e. there was no other polymeric component.

The use of component A by itself as the hot-melt adhesive provided a bond with a good 180° Peel Strength but the failure type was adhesive failure i.e. the failure of the bond was between the adhesive and the substrate. Such a failure was deemed to be unacceptable.

The adhesive containing component C as polymeric component showed an acceptable 180° Peel Strength with cohesive failure but the creep test was a failure. Thus, this adhesive was also deemed to be unacceptable.

The remaining adhesive compositions shown in Table I were acceptable in both 180° peel strength and in the creep test.

#### EXAMPLE II

Blends of (i) a random copolymer of propylene with 4% of ethylene as comonomer and having a melt flow index of 5 dg/min and (ii) an

ethylene/vinyl acetate copolymer containing 28% by weight of vinyl acetate comonomer and having a melt index of 800 dg/min, were grafted with maleic anhydride using a melt grafting process and a free radical initiator.

Further details and the results obtained are given in Table II. The creep test and 180° peel tests were carried out according to the procedures outlined in Example I, using PET fabric.

In Run 1, the blend contained 10% of the ethylene/vinyl acetate copolymer, and had a graft level of 0.9%. In Run 2, the blend contained 20% of the ethylene/vinyl acetate copolymer, and had a graft level of 0.8%.

The results show that a composition that was blended and then grafted passed the creep and 180° peel tests.

#### EXAMPLE III

The procedure of Run 2 was repeated, except that maleic anhydride was not fed to the extruder. The results obtained are given in Table II as Run 3.

The results show that the composition passed the creep and 180° peel tests.

TABLE II

Run No.	Substrate	180° Peel Strength	Failure Type	Creep Test
1	PET fabric	34	cohesive	passed
2	PET fabric	29	cohesive	passed
3	PET fabric	24	cohesive	passed

## CLAIMS:

1. An adhesive composition comprising a melt blend of:

(a) 50-95% by weight of polypropylene that has been grafted with 0-5% by weight of at least one ethylenically-unsaturated carboxylic acid or anhydride, or derivative thereof; and

(b) 5-50% by weight of at least one copolymer of ethylene and at least one comonomer selected from carbon monoxide, vinyl acetate, alkyl acrylates, alkyl methacrylates, in which the alkyl group has 1-4 carbon atoms, acrylic acid and methacrylic acid, and ethylene/propylene/diene copolymers, said ethylene/propylene/diene copolymer having a Mooney viscosity of less than 20 at 125°C, said copolymer having been grafted with 0-5% by weight of at least one ethylenically-unsaturated carboxylic acid or anhydride, or derivative thereof.

2. The composition of Claim 1 in which the blend is in the form of a melt blend.

3. The composition of Claim 1 in which the polymer of (a) has a melt index in the range of 100-500 dg/min.

4. The composition of any one of Claims 1-3 in which the polymer of (a) or (b) is a grafted polymer.

5. The composition of any one of Claims 1-3 in which the polymers of (a) and (b) are grafted polymers.

6. The composition of Claim 4 or Claim 5 in which grafted polymer (b) has a melt index of at least 100 dg/min.

7. The composition of any one of Claims 1-6 in which the polymer of (b) has been grafted with 0.5-2.0% by weight of the ethylenically unsaturated carboxylic acid or anhydride, or derivative thereof.

8. An adhesive composition comprising a blend of:

- (a) 50-95% by weight of polypropylene; and
- (b) 5-50% by weight of at least one

5 copolymer of ethylene and at least one comonomer selected from carbon monoxide, vinyl acetate, alkyl acrylates, alkyl methacrylates, in which the alkyl group has 1-4 carbon atoms, acrylic acid and methacrylic acid, and ethylene/propylene/diene  
10 copolymers, said ethylene/propylene/diene copolymer having a Mooney viscosity of less than 20 at 125°C, said blend having been grafted with up to 5% by weight of at least one ethylenically-unsaturated carboxylic acid or anhydride, or  
15 derivative thereof.

9. The composition of Claim 8 in which the adhesive composition contains un-grafted ethylene/vinyl acetate copolymer or ethylene/propylene/diene copolymer.

20 10. The composition of Claim 9 in which the composition contains ungrafted copolymer in the presence of grafted polymer of (b).

11. The composition of any one of Claims 8-10 in which the polymer of (b) is selected from  
25 ethylene/vinyl acetate copolymers, ethylene/(meth) acrylate copolymers, ethylene/(meth) acrylic acid copolymers, and copolymers of ethylene, alkyl acrylate and carbon monoxide.

12. The composition of any one of Claims  
30 1-11 in which the melt viscosity of the composition is 1000-100 000 cps at 220°C.

13. The composition of Claim 12 in which the melt viscosity is 10 000-75 000 cps at 220°C.

14. The composition of Claim 12 in which  
35 the melt viscosity is 20 000-50 000 cps at 220°C.

15. The composition of any one of Claims 1-14 in which the polymer of (a) has been grafted



with at least 0.1% by weight of said at least one ethylenically unsaturated carboxylic acid or anhydride, or derivative thereof.

16. The composition of any one of Claims 1-14 in which the polymer of (a) has been grafted with at least 0.5% by weight of said at least one ethylenically unsaturated carboxylic acid or anhydride, or derivative thereof.

17. A process for the bonding of a first substrate to a second substrate comprising coating the first substrate with a molten composition of a blend of:

(a) 50-95% by weight of polypropylene that has been grafted with 0-5% by weight of at least one ethylenically-unsaturated carboxylic acid or anhydride, or derivative thereof; and

(b) 5-50% by weight of at least one copolymer of ethylene and at least one comonomer selected from carbon monoxide, vinyl acetate, alkyl acrylates, alkyl methacrylates, in which the alkyl group has 1-4 carbon atoms, acrylic acid and methacrylic acid, and ethylene/propylene/diene copolymers, said ethylene/propylene/diene copolymer having a Mooney viscosity of less than 20 at 125°C, said copolymer having been grafted with 0-5% by weight of at least one ethylenically-unsaturated carboxylic acid or anhydride, or derivative thereof;

contacting the second substrate with the molten adhesive and cooling the resultant bonded structure.

18. A process for the bonding of a first substrate to a second substrate comprising coating the first substrate with a molten composition of a blend of:

(a) 50-95% by weight of polypropylene and

(b) 5-50% by weight of at least one copolymer of ethylene and at least one comonomer

selected from carbon monoxide, vinyl acetate, alkyl acrylates, alkyl methacrylates, in which the alkyl group has 1-4 carbon atoms, acrylic acid and methacrylic acid, and ethylene/propylene/diene copolymers, said ethylene/propylene/diene copolymer having a Mooney viscosity of less than 20 at 125°C; said blend having been grafted with 0-5% by weight of at least one ethylenically-unsaturated carboxylic acid or anhydride;

10                   contacting the second substrate with the molten adhesive and cooling the resultant bonded structure.

19. The process of Claim 17 or Claim 18 in which the blend has been grafted with 0.5-2.0% by weight of at least one ethylenically-unsaturated carboxylic acid or anhydride.

20. The process of any one of Claims 17-19 in which at least one substrate is formed from polypropylene.

21. The process of any one of Claims 17-19 in which both of the substrates are formed from polypropylene.

22. The process of Claim 20 or Claim 21 in which the polypropylene substrate is selected from mineral-filled, foamed or woven polypropylene.

23. The process of any one of Claims 17-22 in which the melt viscosity is 1000-100 000 cps at 220°C.

24. The process of Claim 23 in which the melt viscosity is 10 000-75 000 cps at 220°C.

25. The process of Claim 23 in which the melt viscosity is 20 000-50 000 cps at 220°C.

# INTERNATIONAL SEARCH REPORT

Inter. Application No  
PCT/CA 95/00132

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 6 C09J123/10 C09J151/06

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 6 C09J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US,T,972 002 (D.P.FLORES ET AL) 4 July 1978 see the whole document ---	1-4, 6, 17-25
X	EP,A,0 370 786 (MITSUI TOATSU) 30 May 1990 see page 3, line 12 - line 52 ---	1-25
X	WO,A,93 11175 (QUANTUM CHEMICAL) 10 June 1993 see page 6, line 1 - page 19, line 4 -----	1-25

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

- \* "A" document defining the general state of the art which is not considered to be of particular relevance
- \* "E" earlier document but published on or after the international filing date
- \* "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \* "O" document referring to an oral disclosure, use, exhibition or other means
- \* "P" document published prior to the international filing date but later than the priority date claimed

- \* "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \* "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \* "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \* "&" document member of the same patent family

Date of the actual completion of the international search

3 May 1995

Date of mailing of the international search report

06.06.95

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+ 31-70) 340-3016

Authorized officer

Schmidt, H

# INTERNATIONAL SEARCH REPORT

International Application No  
PCT/CA 95/00132

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-T-972002		NONE	
EP-A-370786	30-05-90	JP-A- 2140280	29-05-90
WO-A-9311175	10-06-93	US-A- 5367022	22-11-94
		AU-A- 3149493	28-06-93